PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent

appln. of:

Michio HORIUCHI

et al.

Serial No:

Not yet assigned

Filed:

Herewith

For:

WIRING SUBSTRATE, METHOD OF MANUFACTURING SAME, AND

SEMICONDUCTOR DEVICE

Examiner:

Not yet assigned

Art Unit:

Not yet assigned

Docket No.:

089-01

Certificate of Mailing by Express Mail

"Express Mail" Mailing Label No. EL018405275US

Date of Deposit: April 5, 2001

I hereby certify that this paper or fee and the papers indicated as being transmitted therewith are being deposited with the United States Postal Service as "Express Mail Post Office to Addressee" in an envelope addressed to the Commissioner for Patents, Washington, DC. 20231.

Typed or printed name of person making deposit: Ourmazd S. Ojan

eposit: Ourmazd S. Ojan

Signature of person making deposit

Box Patent Application

Commissioner for Patents Washington, D.C. 20231

PRELIMINARY AMENDMENT

Sir:

This preliminary amendment relates to the above-reference patent application. Kindly enter this preliminary amendment prior to calculation of the filing fee.

Please enter the following amendment without prejudice:
IN THE CLAIMS:

Amend claims 3-6 and 9 as follows:

- -3.(amended) A wiring substrate according to claim 2, in which the low-elasticity underlayer is made of a material having a Young's modulus of less than 1 GPa measured at a room temperature

1

ħ

(20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C.

4. (amended) A wiring substrate according to claim 3, in which the rerouted wiring is covered with a solder resist layer, and the solder resist layer is made of a resist material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C.

5. (amended) A wiring substrate according to claim 4, in which the low-elasticity underlayer extends between the base material of the wiring substrate and the external-connection terminal, the low-elasticity underlayer in the region of the electronic-part mounting pad and the rerouted wiring has a thickness of 50 μ m or more, and the low-elasticity underlayer in the region of the external-connection terminal has a thickness of 10 μ m or less.

6. (amended) A wiring substrate according to claim 5, in which the rerouted wiring is formed in a nonlinear pattern, at least, between the electronic-part mounting pad and the external-connection terminal.

9.(amended) A method of manufacturing a wiring substrate according to claim 8, which comprises the steps of:

Ad

forming a low-elasticity underlayer from a material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C, on the base material of the wiring substrate;

19825512 Duis

forming a through-hole that extends from the upper surface of the low-elasticity underlayer to the rerouted wiring on the base material located at the lower surface of the low-elasticity underlayer, at a predetermined position of the low-elasticity underlayer; and

forming, by plating, a connection via-hole in the through-hole, the electronic-part mounting pad, and the rerouted wiring. - -

Add new claims 13-23 as follows:

- - 13. A wiring substrate according to claim 1 in which the low-elasticity underlayer is made of a material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C.
- 14. A wiring substrate according to claim 1, in which the rerouted wiring is covered with a solder resist layer, and the solder resist layer is made of a resist material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C.
- 15. A wiring substrate according to claim 2, in which the rerouted wiring is covered with a solder resist layer, and the solder resist layer is made of a resist material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C.

16. A wiring substrate according to claim 1 in which the low-elasticity underlayer extends between the base material of the wiring substrate and the external-connection terminal, the low-elasticity underlayer in the region of the electronic-part mounting pad and the rerouted wiring has a thickness of 50 μm or more, and the low-elasticity underlayer in the region of the external-connection terminal has a thickness of 10 μm or less.

- 17. A wiring substrate according to claim 2 in which the low-elasticity underlayer extends between the base material of the wiring substrate and the external-connection terminal, the low-elasticity underlayer in the region of the electronic-part mounting pad and the rerouted wiring has a thickness of 50 μ m or more, and the low-elasticity underlayer in the region of the external-connection terminal has a thickness of 10 μ m or less.
- 18. A wiring substrate according to claim 3 in which the low-elasticity underlayer extends between the base material of the wiring substrate and the external-connection terminal, the low-elasticity underlayer in the region of the electronic-part mounting pad and the rerouted wiring has a thickness of 50 μ m or more, and the low-elasticity underlayer in the region of the external-connection terminal has a thickness of 10 μ m or less.
- 19. A wiring substrate according to claim 1 in which the rerouted wiring is formed in a nonlinear pattern, at least, between the electronic-part mounting pad and the external-connection terminal.

20. A wiring substrate according to claim 2 in which the rerouted wiring is formed in a nonlinear pattern, at least, between the electronic-part mounting pad and the external-connection terminal.

Cont A3

- 21. A wiring substrate according to claim 3 in which the rerouted wiring is formed in a nonlinear pattern, at least, between the electronic-part mounting pad and the external-connection terminal.
- 22. A wiring substrate according to claim 4 in which the rerouted wiring is formed in a nonlinear pattern, at least, between the electronic-part mounting pad and the external-connection terminal.
- 23. A method of manufacturing a wiring substrate according to claim 7, which comprises the steps of:

forming a low-elasticity underlayer from a material having a Young's modulus of less than 1 GPa measured at a room temperature (20 to 30 °C) and a Young's modulus of 10 MPa or less measured at 150 °C, on the base material of the wiring substrate;

forming a through-hole that extends from the upper surface of the low-elasticity underlayer to the rerouted wiring on the base material located at the lower surface of the low-elasticity underlayer, at a predetermined position of the low-elasticity underlayer; and

forming, by plating, a connection via-hole in the through-hole, the electronic-part mounting pad, and the rerouted wiring. --

REMARKS

Claims 1-23 are in the application.

The claims have been amended to more particularly point out and distinctly claim applicants' invention by simplifying the dependencies of the dependent claims, and to conform the claims to U.S. practice.

Early and favorable action on the merits of the application are earnestly solicited.

Respectfully submitted,

Date: April 5, 2001

Ourmazd S. Ojan

Registration No. 38,065

Paul and Paul

2900 Two Thousand Market Street

Philadelphia, PA 19103

(215) 568-4900

Order No.:0253